



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 1 页, 共 9 页

客户信息	委托单位 : 上海闵行区诺达双语学校		
样品描述	三条藏青色/湖蓝色针织拼接运动长裤		
客户认定信息	商标 : AKOA 生产单位 : 江苏苏美达伊顿纪德品牌管理有限公司 客供成分 : 面料: 聚酯纤维 100% 样品名称 : 运动春秋款长裤·藏青湖蓝		
样品获取	送样		
收样日期	2026-07-22	测试日期	2026-07-23~2026-07-27
检验性质	委托检测	报告签发日期	2026-07-27
判定依据	- GB 18401-2010 《国家纺织产品基本安全技术规范》 B 类 - GB 31701-2015 《婴幼儿及儿童纺织产品安全技术规范》 B 类 - GB/T 29862-2013 《纺织品 纤维含量的标识》 - GB/T 31888-2015 《中小学生校服》		
综合检验结论	检验结果及单项判定见下页。		
样品呈现	见末页。		

批准:

吴海霞

制单:

陈秋芳



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 2 页, 共 9 页

综合检验结论

序号	项目	判定依据	判定结果
1	接缝强力(成衣面料)	GB/T 31888-2015	合格
2	接缝强力(成衣里料)	GB/T 31888-2015	不适用
3	接缝处纱线滑移(机织类)	GB/T 31888-2015	不适用
4	异味	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
5	绳带(7 岁及以上儿童服装)	GB 31701-2015 B 类 GB/T 31888-2015	合格
6	产品上金属针等锐利物	GB 31701-2015 B 类 GB/T 31888-2015	合格
7	附件锐利性	GB 31701-2015 B 类 GB/T 31888-2015	合格
8	纤维含量	GB/T 29862-2013	合格
9	耐水色牢度	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
10	耐水色牢度 (湖蓝色拼块)	--	--
9	耐汗渍色牢度	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
10	耐汗渍色牢度 (湖蓝色拼块)	--	--
11	耐摩擦色牢度	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
12	耐摩擦色牢度 (湖蓝色拼块)	--	--
13	耐皂洗色牢度	GB/T 31888-2015	合格
14	耐光色牢度	GB/T 31888-2015	合格
15	耐光、汗复合色牢度	GB/T 31888-2015	不适用
16	断裂强力(机织类)	GB/T 31888-2015	不适用
17	顶破强力(针织类)	GB/T 31888-2015	合格

地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co , Ltd . within 15 days since receiving this report.

检验检测专用章



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 3 页, 共 9 页

18	胀破强力(毛针织类)	GB/T 31888-2015	不适用
19	pH 值	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
20	甲醛含量	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
21	可分解致癌芳香胺染料	GB 18401-2010 B 类 GB 31701-2015 B 类 GB/T 31888-2015	合格
22	起球	GB/T 31888-2015	合格
23	燃烧性能	GB 31701-2015 B 类 GB/T 31888-2015	不适用



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 4 页, 共 9 页

检测项目		技术要求	检验结果
√ [1.成衣]			
绳带(7 岁及以上儿童服装)(GB 31701-2015)			
测试样品尺码		170/72	
表 3	表 3-1	头部和颈部调整服装尺寸的绳带不应有自由端，其他绳带不应有长度超过 75mm 的自由端。 头部和颈部：当服装平摊至最大尺寸时不应有突出的绳圈，当服装平摊至合适的穿着尺寸时突出的绳圈周长不应超过 150mm；除肩带和颈带外，其他绳带不应使用弹性绳带。	N/A
	表 3-3	固着在腰部的绳带，从固着点伸出的长度不应超过 360mm。	符合
	表 3-4	短袖袖子平摊至最大尺寸时，袖口处绳带的伸出长度不应超过 140mm。	N/A
	表 3-5	除腰带外，背部不应有绳带伸出或系着。	符合
	表 3-6	长袖袖口处的绳带扣紧时应完全置于服装内。	N/A
	表 3-7	长至臀围线以下的服装，底边处的绳带不应超出服装下边缘。长至脚踝处的服装，底边处的绳带应该完全置于服装内。	符合
	表 3-8	除了第 1 项～第 7 项以外，服装平摊至最大尺寸时，伸出的绳带长度不应超过 140mm。	符合
	表 3-9	绳带的自由末端不允许打结或使用立体装饰物。	符合
	表 3-10	两端固定且突出的绳圈的周长不应超过 75mm，平贴在服装上的线圈（例如：串带）其两固定端的长度不应超过 75mm。	N/A
综合结论		符合	
备注：	“N/A”表示无或不适用。		



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 5 页, 共 9 页

测试项目 (计量单位) [样品标识]	测试方法 (参数说明)	技术要求 (备注)	测试结果	判定
√ [1.成衣]				
接缝强力 (成衣面料) (N)	GB/T 31888-2015 条款 5.20 (GB/T 8629-2001 洗涤程序 5A, 一次洗涤, 悬挂晾干。)	裤后裆缝接缝强力 $\geq$ 140	裤后裆缝接缝强力 450	合格
接缝强力 (成衣里料) (N)	GB/T 31888-2015 条款 5.20	--	不适用	--
接缝处纱线滑移 (机 织类) (mm)	GB/T 31888-2015 条款 5.21	--	不适用	--
异味	GB 18401-2010 条款 6.7	无	无	合格
产品上金属针等锐利 物	GB 31701-2015 条款 4.5.2	产品上不允许残留金 属针等锐利物	无锐利物	合格
附件锐利性	GB/T 31702-2015	婴幼儿及儿童纺织产 品所用附件不应存在 可触及的锐利尖端和 锐利边缘	-可触及的锐利尖端 无 -可触及的锐利边缘 无	合格
√ [2.藏青色面料]				
纤维含量 (%)	FZ/T 01057.2-2007 FZ/T 01057.3-2007 FZ/T 01057.4-2007	聚酯纤维 100[$\pm$ 0]	聚酯纤维 100	合格
耐水色牢度 (级)	GB/T 5713-2013	变色 $\geq$ 3-4 沾色 $\geq$ 3-4	变色 4-5 沾色 -棉 4-5 -聚酯纤维 4-5	合格
耐汗渍色牢度 (级)	GB/T 3922-2013	酸性:变色 $\geq$ 3-4 酸性:沾色 $\geq$ 3-4 碱性:变色 $\geq$ 3-4 碱性:沾色 $\geq$ 3-4	(酸性)(碱性) 变色 4-5 4-5 沾色 -棉 4-5 4-5 -聚酯纤维 4-5 4-5	合格
耐摩擦色牢度 (级)	GB/T 3920-2008	干摩擦 $\geq$ 3-4 湿摩擦 $\geq$ 3	干摩擦 4-5 湿摩擦 4-5	合格
耐皂洗色牢度 (级)	GB/T 3921-2008 方法 A (1) (洗涤温度 40°C, 洗涤时间 30 分钟, 5g/L 皂片洗涤液)	变色 $\geq$ 3-4 沾色 $\geq$ 3-4	变色 4-5 沾色 -棉 4-5 -聚酯纤维 4-5	合格
耐光色牢度 (级)	GB/T 8427-2008 方法 3, 参考 4 级蓝色羊毛标样	$\geq$ 4	>4	合格

地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.





中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 6 页, 共 9 页

测试项目(计量单位) [样品标识]	测试方法 (参数说明)	技术要求 (备注)	测试结果	判定
耐光、汗复合色牢度 (级)	GB/T 14576-2009	--	不适用	--
断裂强力(机织类) (N)	GB/T 3923.1-2013 条样法 (CRE 试验仪, 测试速度 100mm/min, 初始隔距 200mm)	--	不适用	--
顶破强力(针织类) (N)	GB/T 19976-2005 钢球直径 38mm (CRE 拉伸测试仪, 测试速度 300mm/min, 弹子直径为 38mm)	≥ 250	1118	合格
胀破强力(毛针织类) (kPa)	GB/T 7742.1-2005 膜片胀破 法 (试验面积 7.3c m², 胀破时间 (20±5)s)	--	不适用	--
pH 值	GB/T 7573-2009 (萃取介质: 0.1mol/L 氯化钾溶 液)	4.0~8.5	6.5	合格
甲醛含量 (mg/kg)	GB/T 2912.1-2009 水萃取法	≤ 75	未检出	合格
	备注: 1) “未检出”指小于检出限; 2) 检出限: 20mg/kg。			
可分解致癌芳香胺染 料 (mg/kg)	GB/T 17592-2024 GC-MS 分析 方法	禁用(≤ 20)	未检出	合格
	备注: 1) “未检出”指小于定量限; 2) 定量限: 5mg/kg; 3) 禁用芳香胺物质清单见附页。			
起球 (级)	GB/T 4802.1-2008 圆轨迹法, 参数 E (压力 780cN, 起毛 0 次, 起 球 600 次)	≥ 3-4	4-5	合格
燃烧性能	GB/T 14644-2014 45°方向燃 烧速率	--	不适用	--



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 7 页, 共 9 页

测试项目（计量单位） [样品标识]	测试方法 （参数说明）	技术要求 （备注）	测试结果	判定
√ [3.湖蓝色拼块]				
纤维含量（%）	FZ/T 01057.2-2007 FZ/T 01057.3-2007 FZ/T 01057.4-2007	聚酯纤维 100[±0]	聚酯纤维 100	合格
耐水色牢度（级）	GB/T 5713-2013	--	未检测	--
耐汗渍色牢度（级）	GB/T 3922-2013	--	未检测	--
耐摩擦色牢度（级）	GB/T 3920-2008	--	未检测	--
pH 值	GB/T 7573-2009 （萃取介质：0.1mol/L 氯化钾溶液）	4.0~8.5	6.1	合格
甲醛含量（mg/kg）	GB/T 2912.1-2009 水萃取法	≤ 75	未检出	合格
	备注：1) “未检出”指小于检出限； 2) 检出限：20mg/kg。			
可分解致癌芳香胺染料（mg/kg）	GB/T 17592-2024 GC-MS 分析方法	禁用(≤ 20)	未检出	合格
	备注：1) “未检出”指小于定量限； 2) 定量限：5mg/kg； 3) 禁用芳香胺物质清单见附页。			
备注	1. 本实验室根据客户要求完成以上检测内容，本检测报告的结果仅适用于来样。 2. 本实验室不对客户认定信息真实性负责。 3. 标记"--"的测试项目表示不予判定或不具备判定条件。 4. 除非客户要求，本报告不考虑测量结果的不确定度。			



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 8 页, 共 9 页

附页:

No. (编号)	CAS No. (化学文摘编号)	Chemical Name (化学名称)
1	92-67-1	4-aminobiphenyl (4-氨基联苯)
2	92-87-5	benzidine (联苯胺)
3	95-69-2	4-chloro-o-toluidine (4-氯邻甲苯胺)
4	91-59-8	2-naphthylamine (2-萘胺)
5	97-56-3	o-aminoazotoluene (邻氨基偶氮甲苯)
6	99-55-8	5-nitro-o-toluidine (5-硝基-邻甲苯胺)
7	106-47-8	p-chloroaniline (对氯苯胺)
8	615-05-4	2,4-diaminoanisole (2,4-二氨基苯甲醚)
9	101-77-9	4,4'-diaminobiphenylmethane (4,4'-二氨基二苯甲烷)
10	91-94-1	3,3'-dichlorobenzidine (3,3'-二氯联苯胺)
11	119-90-4	3,3'-dimethoxybenzidine (3,3'-二甲氧基联苯胺)
12	119-93-7	3,3'-dimethylbenzidine (3,3'-二甲基联苯胺)
13	838-88-0	3,3'-dimethyl-4,4'-diaminobiphenylmethane (3,3'-二甲基-4,4'-二氨基二苯甲烷)
14	120-71-8	p-cresidine (2-甲氧基-5-甲基苯胺)
15	101-14-4	4,4'-methylene-bis- (2-chloroaniline) (4,4'-亚甲基-二- (2-氯苯胺))
16	101-80-4	4,4'-oxydianiline (4,4'-二氨基二苯醚)
17	139-65-1	4,4'-thiodianiline (4,4'-二氨基二苯硫醚)
18	95-53-4	o-toluidine (邻甲苯胺)
19	95-80-7	2,4-toluylenediamine (2,4-二氨基甲苯)
20	137-17-7	2,4,5-trimethylaniline (2,4,5-三甲基苯胺)
21	90-04-0	o-anisidine (邻氨基苯甲醚)
22	60-09-3	4-aminoazobenzene (4-氨基偶氮苯)
23	95-68-1	2,4-xylydine (2,4-二甲基苯胺)
24	87-62-7	2,6-xylydine (2,6-二甲基苯胺)



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co., Ltd. within 15 days since receiving this report.



中国认可
国际互认
检测
TESTING
CNAS L6319



中联品检（上海）技术服务有限公司
United Testing Services (Shanghai) Co., Ltd.

检测报告

防伪查询网址: www.fcl-sz.org.cn
防伪码: 7122507715



报告编号: ZLPJ10189287

第 9 页, 共 9 页

送检样品原样



===== 检测报告结束 =====

中联品检



地址: 上海市松江区鼎源路 618 弄 1 号 29 幢 4、8 层及 1 号 30 幢地下室部分近车位 C005 左侧

Address: 4&8/F. of Building 29, No. 1, and Left Side, Near Parking Space C005, Basement Section, Building 30, No.1, Lane 618, Dingyuan Road, Songjiang District, Shanghai, China

邮编/Post Code: 201616 电话/Tel: 021-67877405 传真/Fax: 021-37657160

若对检测报告有异议, 应于收到报告之日起 15 日内向检测单位提出, 逾期不予受理。

Disagreement against the reports, if any, should be offered to United Testing Services (Shanghai) Co , Ltd . within 15 days since receiving this report.